

iq.ul.com

PROSPECTOR®

View additional material information including performance and processing data

CLICK TO CONTINUE

The information presented on the UL Prospector datasheet was acquired by UL Prospector from the producer of the material. UL Prospector makes substantial efforts to assure the accuracy of this data. However, UL Prospector assumes no responsibility for the data values and strongly encourages that upon final material selection, data points are validated with the material supplier.

E230779

Component - Plastics

Guide Information

QINGDAO HAIER NEW MATERIAL R & D CO LTD

HAIER INTERNATIONAL ZONE, JIAOZHOU, QINGDAO SHANDONG 266300 CN

FR-201GY(+)

Polyethylene Terephthalate (PET), furnished as pellets

<u>Color</u>	<u>Min. Thk (mm)</u>	<u>Flame Class</u>	<u>HWI</u>	<u>HAI</u>	<u>RTI Elec</u>	<u>RTI Imp</u>	<u>RTI Str</u>
ALL	1.0	V-0	-	-	75	75	75
	2.0-2.2	V-0, 5VA	-	-	75	75	75

Comparative Tracking Index (CTI): -

Dielectric Strength (kV/mm): -

High-Voltage Arc Tracking Rate (HVTR): -

Dimensional Stability (%): -

Inclined Plane Tracking (IPT) kV: -

Volume Resistivity (10^x ohm-cm): -Surface Resistivity (10^x ohm-cm): -

High Volt, Low Current Arc Resis (D495): -

(+)- May be represented seven digits maximum by a combination of letters and/or numbers denoting different clients.

Y - Replaced by two digits from 10 to 45 which indicates glass fiber content from 10% to 45%

ANSI/UL 94 small-scale test data does not pertain to building materials, furnishings and related contents. ANSI/UL 94 small-scale test data is intended solely for determining the flammability of plastic materials used in the components and parts of end-product devices and appliances, where the acceptability of the combination is determined by UL.

Report Date: 2014-07-09

Last Revised: 2014-07-10

© 2019 UL LLC

**IEC and ISO Test Methods**

Test Name	Test Method	Units	Thk (mm)	Value
Flammability	IEC 60695-11-10, IEC 60695-11-20	Class (color)	1.0	V-0 (ALL)
			2.0-2.2	V-0, 5VA (ALL)
Glow-Wire Flammability (GWFI)	IEC 60695-2-12	°C	-	-
Glow-Wire Ignition (GWIT)	IEC 60695-2-13	°C	-	-
IEC Comparative Tracking Index	IEC 60112	Volts (Max)	-	-
IEC Ball Pressure	IEC 60695-10-2	°C	-	-
ISO Heat Deflection (1.80 MPa)	ISO 75-2	°C	-	-
ISO Tensile Strength	ISO 527-2	MPa	-	-
ISO Flexural Strength	ISO 178	MPa	-	-
ISO Tensile Impact	ISO 8256	kJ/m ²	-	-
ISO Izod Impact	ISO 180	kJ/m ²	-	-
ISO Charpy Impact	ISO 179-2	kJ/m ²	-	-